

# GEOGRID GEOCOMPOSITE ENGINEERED FOR HIGH-STRENGTH PAVEMENT STABILISATION

## GEOFABRICS GEOGRID TRITEX GEOCOMPOSITE

### TECHNICAL DATA SHEET

Geofabrics® Geogrid™ Tritex geocomposite combines a premium non-woven geotextile and triaxial geogrid. These products are laminated together to create a high-performance geocomposite.

- Offers separation, filtration and aggregate interlock simultaneously
- Enhanced structural characteristics results in more economical construction, improved performance and longer life
- Improved cost benefits by reducing aggregate layer thickness, the need for excavation and increasing bearing capacity to allow for higher loads
- Applicable to Road & Rail sectors



### GEOFABRICS GEOGRID TRITEX GEOCOMPOSITE TECHNICAL DATA

PROPERTY	TEST METHOD	UNITS	TRITEX 26	TRITEX 27
Polymer			Polypropylene	
Carbon Black Content	ASTM D1603	%	2	
Geogrid Property				
Typical Unit Weight	EOTA TR41 B.3	kg/m <sup>2</sup>	0.25	0.28
Hexagon Pitch	EOTA TR41 B.4	mm	80 (±4)	80 (±4)
Radial Secant Stiffness at 0.5% Strain	EOTA TR41 B.1	kN/m	390 (-75)	480 (-90)
Radial Secant Stiffness Ratio	EOTA TR41 B.1	-	0.8 (-0.15)	0.8 (-0.15)
Radial Secant Stiffness at 2% Strain	EOTA TR41 B.1	kN/m	290 (-65)	360 (-65)
Junction Efficiency	EOTA TR41 B.2	%	100 (-10)	100 (-10)
Geotextile Property				
Polymer			Polyester	
Grab Tensile Strength (Q Value)	AS3706.2	N	≥ 500	
Trapezoidal Tear Strength (Q Value)	AS3706.3	N	≥ 180	
G Rating (Q Value)	Austrroads		≥ 900	
EOS Pore Size O95	AS3706.7	μ	≤ 180	
Flow rate (Q100)	AS3706.9	l/m <sup>2</sup> /s	≥ 50	
Roll Dimensions				
Minimum Roll Width	-	m	3.95	
Minimum Roll Length	-	m	50	

#### Notes:

Characteristic value (Q) = Mean - 0.83 x standard deviation of the lot tested. Non-woven geotextile meets filtration classes 1-4 for TNZ F/7 : Specifications - Geotextiles. All quoted values and dimensions are typical unless stated otherwise.

The values published are to the best of our knowledge true and correct and are obtained through independent and in-house laboratory testing. The product specification may change at any time without prior notice. No warranty is expressed or implied. Manufactured in a facility certified to the ISO 9001 Quality Management System Standard.

VISIT [GEOFABRICS.CO.NZ](http://GEOFABRICS.CO.NZ) OR CALL 0800 60 60 20 (NZ)



**GEOFABRICS®**  
Sustainable solutions