



MACDRAIN SPORT D8 MRT

DRAINAGE COMPOSITE FOR SPORT PITCHES

Geocomposite for planar drainage systems, produced by thermo-bonding a draining core in extruded Polypropylene monofilaments with one filtering nonwoven geotextile - that may also be working as separation or protecting layer - and one laminated layer at the bottom with separation function. The product is supplied in rolls having an edge for the overlap of the laminated layer. Version **D8 MRT SA** is equipped with a self adhesive tape on the edge of the laminated bottom layer, which allows to connect and seal adjacent rolls on site.

Properties	Standard	Unit	Value	Tolerances
Geocomposite				
Thickness at 2 kPa	EN ISO 9863-1	mm	8.0	±10%
Mass per unit area	EN ISO 9864	g/m ²	880	±10%
Tensile strength MD/CMD	EN ISO 10319	kN/m	20/18	±15%
In-plane flow capacity MD	EN ISO 12958	l/(m·s)	See table below	±20%
Hydraulic gradient:				
Contacts:	Load	0.03	1.00	
Soft/soft	20 kPa	-	2.90**	**CE flow
	20 kPa	0.42	3.00	
Soft/rigid	100 kPa	0.24	1.70	
	200 kPa	0.15	1.20	
Filter Layer				
Structure	Mechanically bonded non woven, thermotreated			
Raw material	Polypropylene, UV-stabilized			
Tensile strength MD/CMD	EN ISO 10319	kN/m	7.5	± 20%
Static puncture resistance	EN ISO 12236	N	1300	± 15%
Dynamic perforation resistance	EN ISO 13433	mm	36	± 20%
Flux normal to the plane	EN ISO 11058	l/(m ² ·s)	110	± 30%
Characteristic opening size O ₉₀	EN ISO 12956	micron	100	± 30%
Width	-	cm	200/385/405	± 2 %
Drainage core				
Structure	Three dimensional geomat made by extruded monofilaments arranged in channels parallel to MD direction			
Raw material	Polypropylene UV-stabilised by carbon-black			
Width	-	cm	200/385/405	± 2 %
Separation Layer				
Structure	Woven geotextile coated on both sides			
Raw material	Polypropylene (woven geotextile); polymeric coating			
Tensile strength MD/CMD	EN ISO 10319	kN/m	18/16	± 15%
Width	-	cm	215/400/420	± 2%
Standard Geocomposite sizes				
Width	-	cm	200/385/405	± 2 %
Length	-	m	On demand	-0 m / +1 m



Quality System certified according to
UNI EN ISO 9001:2008

For the optimisation and improvement process of the technical characteristics of the products, the manufacturer reserves the right to modify the standard characteristics of the product without any notice. The informations contained herein are to the best of our knowledge accurate, but since the circumstances and conditions in which it may be used are beyond our control, we do not accept any liability for any loss or damage, however arising, which results directly or indirectly from the use of such information nor we do offer any warranty or immunity against patent infringement.

Test directions: MD = machine direction - CMD = cross machine direction
When a tolerance is displayed, it refers to a 95% confidence level
Durability - Predicted to be durable for a minimum of 25 years in natural soils with 4 < pH < 9 and soil temperatures < 25°C
Product has to be covered within 14 days after installation

Maccaferri Asia (Exports)

Unit 3A - 11, Block B, Phileo Damansara 1, 46350 Petaling Jaya, Selangor, Malaysia
T: (60-3) 7957 8330 F: (60-3) 7957 9080
E-mail: info.asia@maccaferri.com - Web site: maccaferri.com/asia