


bidim[®]

Nonwoven Geotextiles

Characteristic Value Data Sheet



QUALITY - SUPPORT - EXPERTISE



Please read the important notice at the end of this brochure

bidim® Nonwoven Geotextiles

Characteristic Value Data Sheet

All bidim® “A” Range nonwoven, needle-punched geotextiles are made in Australia.

QLD MRTS27 (06/09) & NSW RMS R63 (May 2013 Ed4 Rev 0) & NZ TNZ F/7 (2003)						
A Grade	Strength Class	Grab Tensile Strength	Trapezoidal Tear Strength	G Rating	EOS - Pore Size – O ₉₅	Flow Rate (Q ₁₀₀)
		N	N	-	µm	l/m ² /s
		AS 3706.2	AS 3706.3	Austroads 90	AS 3706.7	AS 3706.9
		Q Value	Q Value	Q Value	Mean	Mean
A14	A	> 500	> 180	> 900	≤ 120	> 50
A19	B	> 700	> 250	> 1,350	≤ 120	> 50
A29	C	> 900	> 350	> 2,000	≤ 120	> 50
A39	D	> 1,200	> 450	> 3,000	≤ 120	> 50
A49	E	> 1,600	> 650	> 4,500	≤ 120	> 50

The data and specifications contained in this table are obtained from the manufacturer’s laboratory testing. To ensure this information is current please contact your local branch of Geofabrics Australasia.

Notes

1. Permittivity / Q₁₀₀ - NSW and NZ ranges do not require characteristic Q values, however QLD Q value specification is met by all bidim® A range geotextiles.
2. Characteristic value (Q) = Mean - 0.83 x standard deviation of the lot tested.
3. All grades meet filtration classes I - VIII for MRTS27 Geotextiles (Separation and Filtration).
All grades meet filtration classes 1- 5 for RMS R63 QA Specification - Geotextiles (Separation and Filtration).
All grades meet filtration classes 1- 4 for TNZ F/7: 2003 Specification for Geotextiles.

GEOFABRICS® is a registered trade mark of Geofabrics Australasia Pty Ltd.

NEW ZEALAND

AUCKLAND
(64) 9 634 6495

HAMILTON
(64) 21 732 178

NAPIER
(64) 21 916 736

CHRISTCHURCH
(64) 3 349 5600

AUSTRALIA

MELBOURNE
(03) 8586 9111

SYDNEY
(02) 8785 8800

NEWCASTLE
(02) 4951 2688

COFFS HARBOUR
(02) 6653 5706

PERTH
(08) 6305 0561

ADELAIDE
(08) 8162 5855

HOBART
(03) 6273 0511

BRISBANE
(07) 3279 1588

TOWNSVILLE
(07) 4774 8222

BUNDABERG
(07) 4155 9968

GOLD COAST
(07) 5594 8600

DARWIN
0407 523 669

0800 60 60 20

(Freephone NZ only)

GEOFABRICS.CO.NZ
GEOFABRICS.COM.AU



The information contained in this brochure is general in nature. In particular the content of this brochure does not take account of specific conditions that may be present at your site. Site conditions may alter the performance and longevity of the product and in extreme cases may make the product wholly unsuitable. Actual dimensions and performance may vary. If your project requires accuracy to a certain specified tolerance level you must advise us before ordering the product from us. We can then advise whether the product will meet the required tolerances. Where provided, installation instructions cover installation of product in site conditions that are conducive to its use and optimum performance. If you have any doubts as to the installation instructions or their application to your site, please contact us for clarification before commencing installation. This brochure should not be used for construction purposes and in all cases we recommend that advice be obtained from a suitably qualified consulting engineer or industry specialist before proceeding with installation. This brochure is current as at the date printed below. Geofabrics New Zealand Ltd may make amendments to this document at any time. Please refer to our website, or contact our nearest sales office to ensure you have the most current version. © Copyright held by Geofabrics New Zealand Ltd. All rights are reserved and no part of this publication may be copied without prior permission.